

Material Safety Data Sheet

#GA-422 HIGH VISCOSITY INSTANT ADHESIVE

GLOBAL ADHESIVES, LLC

LAKE HAVASU CITY ARIZONA

WWW.GLOBALADHESIVES.NET

1. Product Identification

Product Name **GA-422**
Product **HIGH Viscosity Ethyl Grade Cyanoacrylate Adhesives**

2. Composition

Ingredients	CAS#	WT%
Ethyl Cyanoacrylate	7085-85-0	90-99
Poly Methyl Methacrylate	9011-14-7	1-10
Proprietary Additive	Proprietary	4-6
Hydroquinone	12-31-9	.1-1.0

Ingredients That Have Exposure Limits

Exposure Limits (TWA) Ingredients	ACGIH (TLV)	OSHA (PEL)	Other
Ethyl Cyanoacrylate	0.2 ppm TWA	None	None
Hydroquinone	2mg/m (TWA)	2mg/m3TWA	2mg/m3TWA 4mg/m3STEL
Exposure Limits (STEL)			
Ethyl Cyanoacrylate	(4ppm) (18mg.m3)	(4ppm) (16mg/m3)	

3. Hazard Identification

Toxicity Skin contact may cause burns. Bonds skin rapidly.
Skin and eye Irritant
Estimated oral LD more than 5,000 mg/kg.
Estimated dermal LD 50 more than 2,000 mg/kg.

Primary Routes of Entry None Known

Symptoms of Exposure Vapor is irritating to the mucous membrane when above TLV. Prolonged and repeated overexposure to vapors may produce allergic reactions with asthma like symptoms in sensitive individuals.

Existing Conditions Aggravated by Exposure None Known

Target Organs and Other Health Effects

		NTP	Carcinogens IARC	OSHA
Methyl Cyanoacrylate	Allergen, irritant, respiratory	No	No	No
Poly (methyl Methacrylate)	Irritant	No	N/A	No
Hydroquinone	ACGIH animal carcinogen, Blood, bone marrow, central Nervous system, eye, immune System, irritant, liver, skin, Mutagen, thyroid.	No	N/A	No

4. First Aid Measures and Personal Protection

Note: See supplemental page or emergency procedures and additional First Aid information

Ingestion Ingestion is not likely.
Inhalation Remove to fresh air. If symptoms persist, obtain medical attention.
Skin contact Soak in warm water.
Eye contact Flush with water

Personnel protection

Eye Chemical safety glasses or goggles.
Skin Polyethylene gloves and/or aprons. DO NOT use cotton/cloth type gloves
Ventilation Positive draft exhaust ventilation should be provided to maintain vapor concentration levels below TLV.

5. Fire Fighting Measures

Flash Point 160-200° F (Method TCC)
Extinguishing Agents Carbon dioxide, foam, dry chemical.

Special Fire Fighting

Procedures Not available
Hazardous Products Formed by Fire or Thermal Decomp Irritating organic vapors
Unusual Fire or Explosion Hazards None

#GA-422 Page

5. Fire Fighting Measures (cont.)

Explosive Limits

(% by volume in air) Lower Not available

(% by volume in air) Upper Not available

6. Accidental Release Measures

If a spill or leak occurs flood area with water to polymerize (cure) the material. Soak up with an inert absorbent.

7. Handling and Storage

Storage Store below 72°F

Handling Avoid contact with skin and eyes. Avoid breathing vapors.

8. Physical and Chemical Properties

Appearance Clear liquid

Odor Sharp, irritating

Boiling Point More than 300°F

Solubility in Water Polymerized

Specific Gravity 1.05 @ 75°F

Vapor Pressure Less than .2mm @ 75°F

Vapor Density 3

VOC 87.1%; 914.55 g/l (EPA Method 24)

9. Stability and Reactivity

Stability Stable

Hazardous Polymerization Will not occur

Incompatibility Polymerized by contact with water, alcohol, amines, alkalies

Conditions to Avoid Not available

Hazardous Decomposition Products (Non-thermal); None

10. Toxicological Information

Refer to number 3.

11. Ecological Information

No data available.

12. Disposal Considerations

Recommended methods of disposal Polymerize as indicated in number 6. Incinerate following EPA and local regulations.
EPA Hazardous waster number: NH-Not a RCRA Hazardous Waste Material.

13. Transportation information

DOT (49CFR 172) Domestic Ground Transport

Proper Shipping Name Unrestricted (not more than 450 liters) Combustible liquids, n.o.s.(Cyanoacrylates)(more than 450 liters)

Hazard Class or Division Unrestricted (not more than 450 liters)

Identification Number None (not more than one pint)

NA 1993 (more than 450 liters)

Marine Pollutant None

IATA

Proper Shipping Name Unrestricted (not more than one pint)

Aviation regulated liquid, n.o.s., (Cyanoacrylate)(more than one pint)

Class or Division Unrestricted (not more than one pint)

Class 9 (more than one pint)

UN or ID Number None (not more than one pint)

UN 3334 (more than one pint)

14. Regulatory Information

CA Proposition 65: No Prop 65 chemicals known to be present

We believe the information contained herein is current and accurate as of this date of this Material Safety Data Sheet. Since the use of this information and these opinions and the conditions of use of this product are not under the control of Global Adhesives, LLC. Or it's agents or distributors; it is the user's obligation to determine the conditions of safe use of this product. The buyer should conduct its own test of this product before use to determine proper preparation technique and suitability for proposed application. Global Adhesives, LLC. Warrants that the product conforms with Global Adhesives, LLC. Written Specifications, and id free from defects and disclaims all other warranties, expressed or implied and is not responsible for loss claim of damage resulting from the use of it's products.

REV 11/04

LIQUID PROPERTIES

Ester Base	Ethyl-2-cyanoacrylate
Appearance	Clear, colorless
Flashpoint	>81°C
Density	1.05
Shelf Life	12 months, unopened
Viscosity (Brookfield) @ 25°C (Spindle 1, 20rpm)	2,400 cP

POLYMER PROPERTIES

Appearance	Clear, colorless
Softening Point	c. 130°C
Refractive Index, n_D^{20}	1.45
Full Cure Time	24 hours
Solubility	DMF, acetonitrile, acetone

CURED PERFORMANCE

	<i>Cure Speed</i>	
Balsa / Balsa		<5 seconds
Oak / Oak		90-180 seconds
Nitrile / Nitrile		<5 seconds
Neoprene / Neoprene		<5 seconds
EPDM / EPDM		<5 seconds
Steel / Steel		10-20 seconds
PVC / PVC		3-10 seconds
Polycarbonate / Polycarbonate		10-40 seconds

	<i>Shear Strength</i>	
Grit Blasted Steel		>15 N/mm ²
Etched Aluminum		>11 N/mm ²
Nitrile Rubber		>10 N/mm ²
Polycarbonate		>12 N/mm ²

	<i>Tensile Strength</i>	
Grit Blasted Steel		>18 N/mm ²
Nitrile Rubber		>5 N/mm ²
Neoprene Rubber		>5 N/mm ²
EPDM Rubber		>2.5 N/mm ²

PRODUCT STORAGE

Global Adhesives, LLC. cyanoacrylates should ideally be stored in original sealed containers until used. Containers should be stored between 10C and 22C; avoid exposure to strong light and heat sources. Refrigeration prolongs shelf life.

DISCLAIMER

The data contained within the Technical Data Sheet are furnished for information only and are believed to be reliable at the time of issue. We cannot assume responsibility for results obtained by others over whose methods we have no control. It is the responsibility of the user to determine the products suitability for use. Global Adhesives, LLC. and its distributors and agents accept no liability arising out of the use of this information of the products described herein.